



**ECOMORTAR®**  
SUSTAINABLE PURE LIME MORTARS

TECHNICAL DATA SHEET

## FINISH

FINISHING COAT / POINTING MORTAR

## THE BENEFITS

- + VAPOUR PERMEABLE
- + HIGH ELASTICITY
- + DESIGNED FOR TRADITIONAL MASONRY



SEE  
COLOUR  
CHART

25  
KG

BS EN  
998-1



### SUITABLE FOR

- > Rendering, finishing coats
- > Pointing

### PACKAGING

- > 25 kg bag
- > 40 bags per pallet (1T pallet)

### PRODUCT COMPOSITION

Dry mix mortar made with pure NHL, sand and adjuvantation.

### SHELF LIFE & GUARANTEE

One year from production date if protected in the original packaging and stored in dry conditions.  
Manufacturer civil Responsibility.

by

 **SAINT-ASTIER**  
LIME, LIFELONG EXCELLENCE

# FINISH

## FINISHING COAT / POINTING MORTAR



### PERFORMANCE

ESSENTIAL SPECIFICATION		EcoMortar® FINISH	Units
Dry density		1,400	kg/m <sup>3</sup>
Compressive strength	at 7 days	1,2	MPa
	at 28 days	1,9	
	at 90 days	3,6	
Elasticity modulus		5,000	MPa
Vapour permeability		0,85	g/(m <sup>2</sup> .hour.mmHg)
Capillarity		1 to 2	g/(m <sup>2</sup> .min <sup>-1/2</sup> )

### MIXING

Mix for 4 to 5 minutes with a whisk mixer (450 to 500 rpm). High-speed mixers (more than 500 rpm) are not recommended as they can over-mix the product and modify its performance. Manual mixing is not recommended.

### WORKING TEMPERATURE

Not below 8°C or above 30°C. Dampen the substrates the day before and prior to application, allow the surface water to be reabsorbed. Avoid rapid drying due to high temperatures and/or strong winds by covering and curing with a light water mist as necessary. Protect wet mortars from frost for at least 10 days after application. Reseal open bags as soon as possible.

### WATER ADDITION

Granulometry EF: 4.5 to 5 litres per 25 kg bag.

Granulometry TF: 4 to 5 litres per 25 kg bag.

### CONSUMPTION/THICKNESS

**Renders:** 1.6kg per mm of thickness per m<sup>2</sup>.

**Pointing:** 17 linear metres for 10x10mm joints per 25kg bag.

When used as a finishing coat make sure that the base coat is straight, dry and sufficiently hardened to accept the finishing coat.

### HEALTH & SAFETY

Consult safety data sheet for each product before use. Find more information at [stastier.co.uk/working-with-ecomortar/](http://stastier.co.uk/working-with-ecomortar/). Special care should be taken to prevent dust from becoming airborne. The use of ventilation and wet methods are recommended. Always use appropriate safety equipment (gloves, mask, safety shoes...).



by

 **SAINT-ASTIER**  
LIME. LIFELONG EXCELLENCE

**Chaux de Saint-Astier**  
28 bis route de Montanceix - La Jarthe - 24110 Saint-Astier - France  
[stastier.co.uk](http://stastier.co.uk) | [contact\\_uk@saint-astier.com](mailto:contact_uk@saint-astier.com)  
[technical\\_support@saint-astier.com](mailto:technical_support@saint-astier.com)

